

TECHNICAL DATA Masterjet Frontlit 400 gram

COATED FRONTLIT

Item	Unit	Value		Test Method
Base Fabric	Denier	1000DX1000D		(High tenacity yarn) 100%PES
Construction	Weaving/inch	18x13		/
Weight of fabric	Gsm/m2	131±10		DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	269±10		DIN53352 BS3424 Method5B
Total weight	Gsm/m2	400±20		DIN53352 BS3424 Method5A
Thickness	mm	0.32±0.02		DIN EN ISO 2286-3
Width	cm	Up to 500		/
Tensile Strength	N/5cm	Warp	1950	DIN53352 BS3424
		Weft	1550	
Tearing Strength	N	Warp	225	DIN53356 BS3424
		Weft	175	
Adhesion	N/5CM	80		DIN53357 BS3425 Method9B
Temperature Resistance	°C	-20~70		DIN53357 BS3425 Method10
Lacquering	None			
Flammability	Can be applied for B1, B2 or NFPA701			
LOW CADMIUM & HEAVY METALS	Can be applied for Reach Compliance or Cadmium Free			
Conclusions and Announcements	<p>Declaration by GLP: Please choose GLP products suitably according to relative provisions or industrial standards. GLP bears the responsibility for the specified technical and performance data on this page only. GLP is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)</p> <p>Remarks: ‘G’ represents Glossy surface, “M” represents Matte surface, “W/G” represents black back. Could be made as requirements</p>			